

TESCON PRIMER RP

Solvent-free primer for interior and exterior use



Technical data

Substance		
Material	acrylic copolymer, solvent-free	
Attribute	Regulation	Value
Colour		white
Application temperature		-10 °C to 45 °C ; 14 °F to 113 °F
Temperature resistance		permanent -40 °C to 90 °C ; -40 °F to 194 °F
Storage		protect from frost, cool and dry

Area of application

For preparation and improvement of subsurfaces for subsequent adhesion with pro clima adhesive tapes such as TESCO VANA, TESCO PROTECT and adhesive tapes in the EXTONSEAL series. Suitable for wood, wood-fibre boards, masonry, roofs, walls and ground slabs.

Consumption figures

Delivery form	Content	Adhesive tape width	Coverage
Tin	0.75 l	60 mm	~ 60 m; 65 yd
		75 mm	~ 45 m; 49 yd
		150 mm	~ 22 m; 24 yd
Tin	2.5 l	60 mm	~ 185 m; 200 yd
		75 mm	~ 150 m; 164 yd
		150 mm	~ 75 m; 82 yd
Dispenser bottle	1 l	60 mm	~ 75 m; 82 yd
		75 mm	~ 60 m; 65 yd
		150 mm	~ 30 m; 33 yd

The quantity used may vary depending on the substrate and application method.

Advantages

- ✓ Secure bonds: penetrates deep and strengthens dusty subsurfaces or subsurfaces with insufficient stability
- ✓ Saves time: no drying time is necessary on absorbent subsurfaces
- ✓ More flexible work: use on dry and slightly moist subsurfaces
- ✓ Can be applied and spread with just one hand using the application bottle
- ✓ Can be used at any time of the year: can also be applied during frosty conditions
- ✓ Excellent values in the hazardous substance test, has been tested according to the ISO 16000 evaluation scheme, solvent-free

Substrates

Before primer is applied, clean the subsurfaces.

Frozen and soaked subsurfaces are not suitable for the application of primer. There must be no water-repellent substances (e.g. grease or silicone) on the subsurface.

All mineral surfaces (e.g. plaster or concrete) and (used) timber subsurfaces can be pretreated. It is also possible to strengthen porous materials such as wood fibre underlay panels.

Permeable absorbent subsurfaces (e.g. wood fibre underlay panels) may be slightly moist. In this case, the adhesive tape to be used can be stuck directly onto primer that is still wet. The product achieves its final level of strength only when it has dried. It may be advisable to use covers to protect the area that has been treated. Primer that has not yet fully dried must be protected against the effects of the weather.

If butyl rubber tapes (e.g. EXOSEAL range) that hinder diffusion are stuck onto relatively well-sealed, non-absorbent subsurfaces (e.g. concrete), the primer must first be allowed to fully dry before the adhesive tape is put in place.

Only ORCON CLASSIC or ORCON MULTIBOND can be used when applying primer for joint adhesives. The primer and ORCON CLASSIC must be fully dried (1-2 days) before the membrane material is stuck in place (dry process).

The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about the application and construction can be found in the pro clima planning documentation. For queries please call the pro clima technical hotline on +49 (0)6202 278245.

MOLL
bauökologische Produkte GmbH
Rheinalstraße 35 - 43
D-68723 Schwetzingen
Fon: +49 (0) 62 02 - 27 82.0
eMail: info@proclima.de



General conditions

Shake or stir the can well before use. One litre of primer can be used to treat an area of about 4.5 m² (48 ft²).

For particularly quick and easy application insert the 1-litre dispenser bottle in to the TENAPP application tool.

Advantages: Application and distribution in just one step, using just one hand and no contamination of the primer in the container.



*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions)



The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about the application and construction can be found in the pro clima planning documentation. For queries please call the pro clima technical hotline on +49 (0)6202 278245.

MOLL
bauökologische Produkte GmbH
Rheintalstraße 35 - 43
D-68723 Schwetzingen
Fon: +49 (0) 62 02 - 27 82.0
eMail: info@proclima.de

